



**PEMERIKSAAN BUTIRAN YANG LOLOS AYAKAN NO. 200 /
 UJI KANDUNGAN LUMPUR DALAM PASIR
 (SNI 03-4142-1996)**

Ukuran Butir Maksimum	Berat Minimum	Keterangan
4,80 mm	500 gram	Pasir
9,60 mm	1000 gram	Kerikil
19,20 mm	1500 gram	Kerikil
38,00 mm	2500 gram	Kerikil

Uraian	Hasil Pengamatan		
	Sampel 1	Sampel 2	Rata-rata
Berat Agregat Kering Oven (W1) gram	500	500	500
Berat Agregat Kering Oven Setelah Dicuci (W2) gram	480.75	494.75	487.75
Persentase Yang Lolos Ayakan No 200 [(W1-W2)/W1]X100%	3.85	1.05	2.45

Diperiksa,
 Laboran

Darussalam, A.Md.

Disetujui,
 Kepala Laboratorium

Ir. Suharyatma, M.T