

*Lampiran 2: Data Penelitian Daya Serap Air*

Komposisi Plastik	Sampel Ke-	Berat Paving Block		Penyerapan Air	Penyerapan Air Rata-rata
		Sebelum dioven	Setelah dioven		
		(kg)	(kg)	(%)	(%)
0%	1	2,589	2,365	9	8
	2	2,527	2,43	4	
	3	2,497	2,412	4	
	4	2,489	2,289	9	
	5	2,52	2,3	10	
0,3%	1	2,652	2,43	9	8
	2	2,523	2,398	5	
	3	2,623	2,397	9	
	4	2,6	2,4	8	
	5	2,4	2,2	9	
0,4%	1	2,592	2,32	12	9
	2	2,495	2,25	11	
	3	2,612	2,42	8	
	4	2,52	2,4	5	
	5	2,55	2,35	9	
0,5%	1	2,575	2,301	12	10
	2	2,522	2,32	9	
	3	2,647	2,4	10	
	4	2,4	2,3	4	
	5	2,5	2,2	14	
0,6%	1	2,53	2,28	11	10

2	2,589	2,398	8
3	2,463	2,178	13
4	2,43	2,23	9
5	2,31	2,11	9