

## LAMPIRAN

Lampiran. 1. Tabel Hasil Pengujian Kuat Tekan

VARIABEL KOMPOSISI	SAMPLE	UKURAN PAVING BLOCK				LUAS PENAMPANG (A) (CM <sup>2</sup> )	LUAS PENAMPANG (A) (MM <sup>2</sup> )	HASIL PENGUJIAN		KUAT TEKAN (MPa)	RATA-RATA KUAT TEKAN (MPa)
		BERAT (KG)	PANJANG (CM)	LEBAR (CM)	TINGGI (CM)			BEBAN MAKSIMUM (KGF)	BEBAN MAKSIMUM (N)		
PLASTIK 0%	1	0.40	6.00	5.70	6.00	34.20	3420	3470.00	34029.08	9.95	10.08
	2	0.40	5.80	5.90	6.00	35.40	3540	3500.00	34323.28	9.70	
	3	0.40	6.00	6.00	6.00	36.00	3600	3230.00	31675.48	8.80	
	4	0.40	6.00	6.00	6.00	36.00	3600	4325.00	42413.76	11.78	
	5	0.40	5.80	5.80	6.00	34.80	3480	2675.00	26232.79	7.54	
	6	0.40	6.00	6.00	6.00	36.00	3600	3550.00	34813.61	9.67	
	7	0.40	5.70	6.00	6.00	36.00	3600	2525.00	24761.79	6.88	
	8	0.40	6.00	6.00	6.00	36.00	3600	4550.00	44620.26	12.39	
	9	0.40	6.00	5.90	6.00	35.40	3540	4025.00	39471.77	11.15	
	10	0.40	6.00	6.00	6.00	36.00	3600	4750.00	46581.59	12.94	
	1	0.40	6.00	5.80	6.00	34.80	3480	4675.00	45846.09	13.17	
	2	0.40	6.00	6.00	6.00	36.00	3600	4880.00	47856.45	13.29	
	3	0.40	6.00	6.00	6.00	36.00	3600	5120.00	50210.05	13.95	
	4	0.40	6.00	6.00	6.00	36.00	3600	4895.00	48003.55	13.33	

VARIABEL KOMPOSISI	SAMPLE	UKURAN PAVING BLOCK				LUAS PENAMPANG (A) (CM2)	LUAS PENAMPANG (A) (MM2)	HASIL PENGUJIAN		KUAT TEKAN (MPa)	RATA-RATA KUAT TEKAN (MPa)
		BERAT (KG)	PANJANG (CM)	LEBAR (CM)	TINGGI (CM)			BEBAN MAKSIMUM (KGF)	BEBAN MAKSIMUM (N)		
PLASTIK 0.3%	5	0.40	6.00	5.80	6.00	34.80	3480	3100.00	30400.62	8.74	12.90
	6	0.40	5.70	6.00	6.00	36.00	3600	3457.00	33901.59	9.42	
	7	0.40	5.60	5.80	6.00	34.80	3480	4990.00	48935.18	14.06	
	8	0.40	6.00	6.00	6.00	36.00	3600	4770.00	46777.72	12.99	
	9	0.40	6.00	5.60	6.00	33.60	3360	5005.00	49082.28	14.61	
	10	0.40	5.70	5.90	6.00	35.40	3540	5567.00	54593.62	15.42	
PLASTIK 0.4%	1	0.40	6.00	6.00	6.00	36.00	3600	5525.00	54181.74	15.05	14.63
	2	0.40	6.00	6.00	6.00	36.00	3600	5800.00	56878.57	15.80	
	3	0.40	5.70	5.80	6.00	34.80	3480	5425.00	53201.08	15.29	
	4	0.40	5.50	5.60	6.00	33.60	3360	5860.00	57466.97	17.10	
	5	0.40	6.00	6.00	6.00	36.00	3600	5112.00	50131.59	13.93	
	6	0.40	5.80	5.80	6.00	34.80	3480	3745.00	36725.90	10.55	
	7	0.40	5.80	6.00	6.00	36.00	3600	5008.00	49111.70	13.64	
	8	0.40	6.00	6.00	6.00	36.00	3600	4925.00	48297.75	13.42	
	9	0.40	5.60	5.90	6.00	35.40	3540	5500.00	53936.58	15.24	
	10	0.40	5.80	5.80	6.00	34.80	3480	5775.00	56633.40	16.27	
	1	0.40	5.80	6.00	6.00	36.00	3600	4060.00	39815.00	11.06	
	2	0.40	5.70	5.80	6.00	34.80	3480	4700.00	46091.26	13.24	
	3	0.40	6.00	5.70	6.00	34.20	3420	4925.00	48297.75	14.12	
	4	0.40	6.00	6.00	6.00	36.00	3600	5500.00	53936.58	14.98	

VARIABEL KOMPOSISI	SAMPLE	UKURAN PAVING BLOCK				LUAS PENAMPANG (A) (CM2)	LUAS PENAMPANG (A) (MM2)	HASIL PENGUJIAN		KUAT TEKAN (MPa)	RATA-RATA KUAT TEKAN (MPa)
		BERAT (KG)	PANJANG (CM)	LEBAR (CM)	TINGGI (CM)			BEBAN MAKSIMUM (KGF)	BEBAN MAKSIMUM (N)		
PLASTIK 0.5%	5	0.40	6.00	5.80	6.00	34.80	3480	3180.00	31185.15	8.96	13.29
	6	0.40	6.00	5.70	6.00	34.20	3420	5115.00	50161.01	14.67	
	7	0.40	6.00	6.00	6.00	36.00	3600	5200.00	50994.58	14.17	
	8	0.40	5.70	5.70	5.80	33.06	3306	4217.00	41354.64	12.51	
	9	0.40	6.00	5.90	6.00	35.40	3540	4995.00	48984.22	13.84	
	10	0.40	6.00	6.00	6.00	36.00	3600	5350.00	52465.58	14.57	
PLASTIK 0.6%	1	0.40	6.00	6.00	6.00	36.00	3600	5450.00	53446.24	14.85	11.58
	2	0.40	6.00	6.00	6.00	36.00	3600	3940.00	38638.20	10.73	
	3	0.40	6.20	6.30	6.00	37.80	3780	4980.00	48837.12	12.92	
	4	0.40	6.00	6.00	6.00	36.00	3600	3680.00	36088.47	10.02	
	5	0.40	6.00	6.00	6.00	36.00	3600	3150.00	30890.95	8.58	
	6	0.40	6.00	5.90	6.00	35.40	3540	3705.00	36333.64	10.26	
	7	0.40	6.10	6.00	6.00	36.00	3600	5680.00	55701.77	15.47	
	8	0.40	6.00	6.00	6.00	36.00	3600	3995.00	39177.57	10.88	
	9	0.40	6.00	5.90	6.00	35.40	3540	4250.00	41678.26	11.77	
	10	0.40	6.00	5.70	5.90	33.63	3363	3525.00	34568.44	10.28	