

Lampiran 3. Mutu Beton

TABEL MUTU BETON K-100 S/D K-350					
Mutu Beton	Semen (kg)	Pasir (kg)	Kerikil (kg)	Air (liter)	w/c ratio
7,4 Mpa K-(100)	247	869	999	215	0,87
9,8 Mpa K-(125)	276	828	1012	215	0,78
12,2 Mpa K-(150)	299	799	1017	215	0,72
14,5 Mpa K-(175)	326	760	1029	215	0,66
16,9 Mpa K-(200)	352	731	1031	215	0,61
19,3 Mpa K-(225)	371	698	1047	215	0,58
21,7 Mpa K-(250)	384	692	1039	215	0,56
24,0 Mpa K-(275)	406	684	1026	215	0,53
26,4 Mpa K-(300)	413	681	1021	215	0,52
28,8 Mpa K-(325)	439	670	1006	215	0,49
31,2 Mpa K-(350)	448	667	1000	215	0,48

Referensi Tabel :
SNI DT - 91 - 0008 - 2007 Tata Cara Perhitungan Harga Satuan Pekerjaan Beton Oleh Dept. Pekerjaan Umum
Written by : <http://www.indragandhi71.com> // indragandhi71@gmail.com // "Tabel Mutu Beton"