

**SINTESIS MAGNETIC BIOCHAR DARI KULIT SALAK UNTUK  
PENURUNAN KADAR KROM LIMBAH PENYAMAKAN KULIT**  
**INTISARI**

MUHAMMAD SHAIHU MUNIR

19612143

Aktivasi, pirolisis sintesis, aplikasi pembentukan  $\text{Fe}_3\text{O}_4/\text{Biochar}$  melalui sistem kombinasi kinetika adsorpsi dengan variasi waktu telah berhasil dilakukan. Penelitian ini dilakukan dengan sintesis *Biochar* kulit dari salak dengan variasi jenis prekursor yaitu  $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$  dan  $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$  sebagai bahan pembentuk  $\text{Fe}_3\text{O}_4$ . Hasil sintesis  $\text{Fe}_3\text{O}_4/\text{Biochar}$  dikarakterisasi menggunakan AAS, FTIR, XRD, TGA, dan VSM. Pada hasil AAS diperoleh waktu optimum terjadi pada waktu 20 menit dengan kapasitas adsorpsi 1216,86 mg/g dan kinetika adsorpsi mengikuti model kinetika pseudo orde 2 dimana diperoleh nilai  $R^2$  yaitu 0.9928. Pada puncak serapan FTIR pada bilangan gelombang 586,34  $\text{cm}^{-1}$  dengan gugus fungsi Fe-O. Pada hasil XRD didapatkan yang mengindikasi pola difraksi partikel magnet fasa  $\text{Fe}_3\text{O}_4$  berdasarkan dengan JCPDS. Pada hasil TGA didapatkan hasil sampel *Biochar* pada suhu kurang dari 200 °C, jika pada suhu diatas 200 °C maka akan habis dan penurunannya sebesar 65,59%. Dan pada hasil VSM sifat kemagnetan yang paling kuat yaitu pada suhu 80 °C dengan magnetit yang memiliki nilai  $\text{Mr}$  3,19 emu/g yang menunjukkan sifat superparamagnetik.

**Kata kunci:** *Biochar*, kromium, adsorpsi

# **SYNTHESIS OF MAGNETIC BIOCHAR FROM SNAKE FRUIT PEEL FOR CHROME REDUCTION OF TANNERY WASTE**

## **ABSTRACT**

MUHAMMAD SHAIHU MUNIR

19612143

Activation, pyrolysis synthesis, application of  $\text{Fe}_3\text{O}_4$ /Biochar formation through a combination system of adsorption kinetics with time variations have been successfully carried out. This research was conducted by synthesizing Biochar from snake fruit peel with various types of precursors, namely  $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$  and  $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$  as  $\text{Fe}_3\text{O}_4$  forming material. The result of  $\text{Fe}_3\text{O}_4$ /Biochar synthesis were characterized using ASS, FTIR, XRD, TGA, and VSM. In the AAS results, the optimum time was obtained at 20 minutes with an adsorption capacity of 1216,86 mg/g and adsorption kinetics following the second-order pseudo kinetics model where the  $R^2$  value of 0,9928 was obtained. FTIR absorption peak at wave number 586,34  $\text{cm}^{-1}$  with Fe-O functional group. In the XRD results obtained which indicates the diffraction pattern of  $\text{Fe}_3\text{O}_4$  phase magnetic particles based on JCPDS. In the TGA results obtained *Biochar* sample results at temperatures less than 200 °C, if at temperature above 200 °C it will run out and the decrease is 65,59%. And in the VSM results, the strongest magnetic properties are at a temperature of 80 °C with magnetic which has a Mr value of 3,19 emu/g which shows superparamagnetic properhties.

**Keywords:** Biochar, chromium, adsorption.